

## STAYCELL ONE STEP® 502 HFO INTUMESCENT SPRAY FOAM

### DESCRIPTION:

**Staycell ONE STEP® 502** is a two-component, self-adhering, seamless, closed-cell, intumescent, spray-applied polyurethane foam system. This product is formulated with highly insulating **HFO** blowing agents and is used to insulate building components such as roof decks, ceilings, walls, siding, structural steel and tanks to provide an integral air barrier / insulation / vapor retarder for building envelope assemblies.

This product has Class A/Class 1 flame spread and smoke developed ratings and is classified as an *Alternative Thermal Barrier Assembly* when installed without thermal barriers, ignition barriers or other fire protective surfaces.

The benefits of **Staycell ONE STEP® 502** include:

- Low GWP
- Superior Insulation
- Air Impermeable at 1"
- Controls Air Infiltration
- Controls Moisture Infiltration
- Structural Enhancement
- Fungal Resistant, per ASTM C1338
- Low VOC per CDPH Standard V 1.2, 2017

### TYPICAL PROPERTIES<sup>(1)</sup>

PROPERTY	METHOD	VALUE
Density, core (pcf @ 2" lifts)	ASTM D 1622	2.0
Compressive Strength (psi)	ASTM D 1621	22
Tensile Strength (psi)	ASTM D 1623	55
Closed Cell Content (%)	ASTM D 6226	>90
Air Permeance (1" @ 75 Pa)	ASTM E 2178	0.002 cfm/ft <sup>2</sup>
Surface Burning Characteristics		
Flame Spread	ASTM E 84	≤ 25
Smoke Developed	ASTM E 84	≤ 450
Potential Heat (Btu/ft <sup>2</sup> /inch)	NFPA 259	1,881
Max Service Temperature		180°F

Exposed spray polyurethane foam is sensitive to ultraviolet light (UV) and will change color over time depending on exposure but can be easily painted with latex paints to color match adjacent surfaces. Contact PSI for paint recommendations.

Polyurethane products manufactured or produced from this liquid system may present a serious fire hazard if improperly used. The character and magnitude of any such hazard will depend on a broad range of factors, which are controlled and influenced by the manufacturing and production process, by the mode of application or installation and by the function and usage of the particular product. **Any flammability rating contained in this literature is not intended to reflect hazards presented by this or any other material under actual fire conditions. These ratings are used solely to measure and describe the product's response to heat and flame under controlled laboratory conditions.** Each person, firm or corporation engaged in the manufacture, production, application, installation or use of any polyurethane product must carefully determine whether there is a potential fire hazard associated with such product in a specific usage and whether such usage complies with the applicable building code.

### R-VALUE AND WATER VAPOR PERMEABILITY<sup>(1)(2)</sup>

Thickness (inches)	R-value <sup>***</sup> (°F·hr·ft <sup>2</sup> / Btu)	Moisture Vapor Permeance <sup>***</sup>
1	5.7	3.48
2	11.3	1.74
3	16.9	1.16
3.5	19.7	0.99
4	22.5	0.87
5	28.1	0.70
6	33.6	0.58
7	39.2	0.50
8	44.7	0.44

<sup>\*</sup>As with all insulating materials, the R-value will vary with age and use conditions.

<sup>\*\*</sup>ASTM C 518

<sup>\*\*\*</sup>ASTM E 96

For proper use of this material, refer to the Staycell ONE STEP® 502 technical data sheet, installation guide and any of the following codes or documents:

- 2012, 2015, 2018 and 2021 International Building Code, Chapter 26 or International Residential Code R316 & R806
- API Fire Safety Guidelines for Use of Rigid Polyurethane and Polyisocyanurate Foam Insulation in Building Construction (AX230)
- SPFA-126 Thermal and Ignition Barriers for the Spray Polyurethane Foam Industry

(1) These physical property values are typical for this material as applied at our development facility under controlled conditions. SPF performance and actual physical properties will vary with differences in application (i.e. ambient conditions, process equipment and settings, material throughput, etc.). As a result, these published properties should be used as guidelines solely for the purpose of evaluation. Physical property specifications should be determined from actual production material. The above data was collected from samples prepared using equipment configurations pertinent to lab conditions.

(2) The data chart shows the R-value of this insulation. "R" means resistance to heat flow. The higher the R-value, the greater the insulating power. Compare insulation R-values before you buy. There are other factors to consider. The amount of insulation will depend upon the climate, the type and size of the building. If you buy too much insulation it will cost you more than what you will save on fuel. To achieve proper R-values, it is essential that this insulation be installed properly.

# STAYCELL ONE STEP® 502 HFO INTUMESCENT SPRAY FOAM INSULATION

## GENERAL INFORMATION:

Staycell ONE STEP® 502 is an intumescent spray polyurethane foam (SPF) intended for installation by qualified contractors trained in the processing and application of SPF systems, as well as the plural-component polyurethane dispensing equipment required to do so. Contractors and applicators must comply with all applicable and appropriate storage, handling, processing and safety guidelines. PSI technical service personnel should be consulted in all cases where application conditions are questionable.

Staycell ONE STEP® 502 has an estimated yield of 4,000 board feet per set. Actual yield performance can be in excess of or below the referenced estimated range based on factors affecting density including, however, not limited to: multiple lifts, substrate texture, substrate temperature, overspray loss, windy conditions, altitude, container residue, equipment characteristics & temperatures, applicator technique, etc. For help estimating yield for this and other spray foams, please consult Spray Polyurethane Foam Alliance's *SPFA-121 SPF Estimating Reference Guide*.

## RECOMMENDED SUBSTRATE TEMPERATURES AND REACTIVITIES:

Minimum substrate and air temp: 40°F. Maximum substrate and air temp: 120°F. For applications below 40°F, contact PSI Technical Services for cold temperature application guidelines.

REACTIVITIES AVAILABLE	AMBIENT TEMPERATURE RANGE
REG	60°F+
FAST	40°F to 60°F

## APPLICATION AND EQUIPMENT INFORMATION:

For detailed technical and application information and instructions, please refer to the installation guide for this product. The proportioning equipment shall be manufactured specifically for heating, mixing and spray application of polyurethane foam and be able to maintain 1:1 metering by volume with +/- 2% variance. All proportioners shall have adequate main heating capacity to deliver heated and pressurized materials up to 150°F. Heated hose shall be able to maintain pre-set temperatures for the full length of the hose. Minimum 2:1 pressure ratio feeder pumps and 3/4 inch supply hoses are required to transfer material from container to the proportioner.

Recommended equipment (contact PSI for more details):

- Graco Reactor or PMC proportioners or equivalent set at 1:1 volume ratio
- Graco Fusion AP or PMC AP-2/AP-3 spray gun with #2 mixing chamber
- Graco T2 2:1 transfer pumps or equivalent

## CAUTIONS AND RECOMMENDATIONS:

Staycell ONE STEP® 502 is designed for an application rate of ½ inch minimum to 4 inches maximum per pass. Once installed and material has cooled it is possible to add additional applications in order to increase the overall installed thickness of SPF. This application procedure is in compliance with the Spray Polyurethane Foam Alliance (SPFA). Staycell ONE STEP® 502 is NOT designed for use as an EXTERIOR roofing system. PSI offers a separate line of products for exterior roofing applications. For more information, please contact your sales representative.

EQUIPMENT SETTING GUIDELINES		
Climate	A side, B side, Hose Temp (Adjust +/- 1° increments)	Proportioner set pressure (Spraying pressure)
Colder	135°F to 145°F	1400-1600 psi (1100-1300 psi)
Warmer	130°F to 140°F	1400-1600 psi (1100-1300 psi)

Cold-storage structures such as coolers and freezers demand special design considerations with regard to thermal insulation and moisture/vapor drive. Staycell ONE STEP® 502 should NOT be installed in these types of constructions unless the structure was designed by a design professional for specific use as cold storage.

In addition to reading and understanding the SDS, all contractors and applicators must use appropriate respiratory, skin and eye Personal Protective Equipment (PPE) when handling and processing polyurethane chemical systems. Personnel should review the following documents published by Spray Polyurethane Foam Alliance (SPFA): *AX-171 Course 101-R Chapter 1: Health, Safety and Environmental Aspects of Spray Polyurethane Foam and Coverings*.  
[www.spraypolyurethane.org](http://www.spraypolyurethane.org)

Also, the following document is available from the Center for the Polyurethanes Industries (CPI): *Model Respiratory Protection Program for Compliance with the Occupational Safety and Health Administration's Respiratory Protection Program Standard 29 C.F.R. §1910.134*.

As with all SPF systems, improper application techniques should be avoided. Examples of improper application techniques include, but are not limited to, excessive thickness of SPF, off-ratio material and spraying into or under rising SPF. Potential results of improperly installed SPF include: dangerously high reaction temperatures that may result in fire and offensive odors that may or may not dissipate. Improperly installed SPF must be removed and replaced with properly installed materials.

Large masses of SPF should be removed to an outside safe area, cut into smaller pieces and allowed to cool before discarding into an appropriate trash receptacle.

SPF insulation is combustible. High-intensity heat sources such as welding or cutting torches must not be used in contact with Staycell ONE STEP® 502. The insulation must not be used in areas that have a maximum service temperature greater than 180°F (82°C).

## SHELF LIFE AND STORAGE CONDITIONS:

Staycell ONE STEP® 502 has a shelf life of approximately six (6) months from the date of manufacture when stored in original, unopened containers at 65°F-85°F. As with all industrial chemicals this material should be stored in a covered, secure location and never in direct sunlight. Storage temperatures above the recommended range will shorten shelf life. Storage temperatures above the recommended range may also result in elevated headspace pressure within packages.

While descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, PSI recommends that the user determine suitability of the product for a particular purpose prior to use. No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth, or that the products, designs, data or information may be used without infringing the intellectual property rights of others. In no case shall the descriptions, information, data or designs provided be considered a part of PSI's terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by PSI hereunder are given gratis and PSI assumes no obligation or liability for the description, designs, data or information given or results obtained, all such being given and accepted at the user's risk.

Warning: These products can be used to prepare a variety of polyurethane products. Polyurethanes are organic materials and must be considered combustible.

# STAYCELL ONE STEP® 502 HFO INTUMESCENT SPRAY FOAM INSULATION

## COMPLIANCE WITH INTERNATIONAL BUILDING CODES (IBC) AND INTERNATIONAL RESIDENTIAL CODES (IRC):

Staycell ONE STEP® 502 and the Staycell® HYBRID HFO System pass the UL 1715 large-scale, enclosed-room fire test listed in the Special Approval subsection of SECTION 2603 of the IBC and SECTION R316 of the IRC when installed exposed as shown in the table below. These assemblies are termed *Alternative Thermal Barrier Assemblies* and are considered acceptable alternates to the ½" gypsum board prescriptive thermal barrier requirements.

Staycell ONE STEP® 502 and the Staycell® HYBRID HFO System are also qualified *Alternative Thermal Barrier Assemblies* when installed in an exposed condition in accordance with ICC 1100-2019 Standard for Spray-Applied Polyurethane Foam Plastic Insulation and IAPMO/ANSI ES 1000-2020 Standard for Building Code Compliance of Spray-Applied Polyurethane Foam based on passing UL 1715.



**LISTING NO. B1020-1**

**Qualification as *Alternative Thermal Barrier Assemblies* when installed exposed; no thermal barrier or ignition barrier required based on compliance with UL1715 large-scale, enclosed-room fire test standard:**

### Staycell ONE STEP® 502 HFO Intumescent Spray Foam Insulation

#### **Exposed applications on walls only:**

Assembly: Staycell ONE STEP® 502 installed at nominal 4 inch or less thickness.

#### **Exposed applications on the underside of roofs/floors/ceilings only:**

Assembly: Staycell ONE STEP® 502 installed at nominal 8.5 inch or less thickness.

Staycell ONE STEP® 502 was fire tested separately for installation exposed on either walls only or the underside of ceilings/roofs only. AS A RESULT, IT IS NOT TO BE INSTALLED EXPOSED ON ENTIRE WALLS AND ENTIRE ROOFS/FLOORS/CEILINGS WHEN ADJACENT TO EACH OTHER. Contact PSI for tested wall/roof transition applications.

### Staycell® HYBRID HFO Intumescent Spray Foam Insulation System

#### **Exposed applications on walls only:**

Assembly: Staycell® 504 base layer installed at nominal 3 inch or less thickness covered with nominal 1 inch thick Staycell ONE STEP® 502 as the exposed surface layer.

#### **Exposed applications on the underside of roofs/floors/ceilings only:**

Assembly: Staycell® 504 base layer installed at nominal 8 inch or less thickness covered with nominal ½ inch thick Staycell ONE STEP® 502 as the exposed surface layer.

The Staycell® HYBRID HFO System was fire tested separately for installation exposed on either walls only or the underside of ceilings/roofs only. AS A RESULT, IT IS NOT TO BE INSTALLED EXPOSED ON ENTIRE WALLS AND ENTIRE ROOFS/FLOORS/CEILINGS WHEN ADJACENT TO EACH OTHER. Contact PSI for tested wall/roof transition applications.

QAI Laboratories, Ltd. (QAI) is accredited by International Accreditation Services, Inc., a division of the International Code Council that publishes the International Building Code and International Residential Code. QAI is accredited for fire testing, quality control inspections of manufacturing facilities and certification of listed and labeled products in accordance with IAS Registration Nos. AA-723, TL-220 and PCA-119.



# STAYCELL ONE STEP® 502 HFO INTUMESCENT SPRAY FOAM INSULATION

TABLE 1

NFPA 285 COMPLYING EXTERIOR WALL ASSEMBLIES

STAYCELL ONE STEP® 502 HFO INTUMESCENT SPRAY FOAM APPLIED IN WALL CAVITY

WALL COMPONENT	MATERIAL DESCRIPTION
Base Wall System – Use either: 1 with the interior, steel studs, minimum 3½-inch depth, minimum No. 20-gauge at a maximum of 24-inch on center with lateral bracing every 4 feet vertically, or 2 or 3	1 - 1 layer of ½-inch thick Type X exterior gypsum sheathing installed on the exterior side of the steel studs 2 - Concrete wall - minimum 2 inch thick 3 - Concrete masonry wall
Floor-Line Firestopping	4 lb/ft <sup>3</sup> mineral wool (e.g. Thermafiber) friction-fit in each wall stud cavity at each floor-line. Mineral wool is not required in stud cavities at floor-line when infill floor-line construction <sup>1</sup> is employed for exterior wall.
Cavity Insulation - Use either 1 or combination of 1 and 2	1 - Full cavity depth or less of Staycell ONE STEP® 502 HFO using sheathing, concrete or masonry as substrate and covering the width of the cavity and inside the stud flange. 2 - Any noncombustible insulation (if batts, can be either faced or unfaced)
Interior Gypsum Wallboard	1 - Minimum ½-inch thick Type X gypsum wallboard
Exterior Wall Covering – Use either 1, 2 or 3 with Note 4.	1 - Any non-combustible exterior wall covering material 2 - Any combustible exterior wall covering system that has successfully been tested in accordance with NFPA 285. 3 - Any combustible exterior wall covering system up to a maximum wall height of 40 feet above grade plane. If the combustible material is fire retardant treated wood, the maximum wall height can be 60 feet above grade plane. 4 - For base wall 2 or 3, a covering is optional but not required. Use an exterior wall covering as described in 1, 2 or 3 above.
Window/Door Perimeters	Framed as required for the base wall. Use No. 25-gauge (minimum) sheet steel for flashing area outside of the base wall.

<sup>1</sup> Infill stud wall construction refers to the condition where the stud framing of an exterior wall is interior to the floor line slab edges, effectively terminating the stud cavity at each floor-line and creating sectioned stud bays in between sequential floors.



# STAYCELL ONE STEP® 502 HFO INTUMESCENT SPRAY FOAM INSULATION

TABLE 2

NFPA 285 COMPLYING EXTERIOR WALL ASSEMBLIES

STAYCELL ONE STEP® 502 HFO INTUMESCENT SPRAY FOAM APPLIED TO EXTERIOR OF WALL ASSEMBLIES

WALL COMPONENT	MATERIAL DESCRIPTION
Base Wall System - Use either 1, 2 or 3	<p>1 - Concrete wall - minimum 2-inch thick</p> <p>2 - Concrete masonry wall</p> <p>3 - One layer of 5/8-inch thick Type X gypsum wallboard on the interior, installed over steel studs: minimum 3 5/8-inch depth, minimum 20-gauge at a maximum of 24 inches on center with lateral bracing every 4 feet vertically.</p>
Floor-Line Firestopping	4 lb/ft <sup>3</sup> mineral wool (e.g. Thermafiber) in each stud cavity and at each floor-line – attached with Z-clips or equivalent. Mineral wool is not required in stud cavities at floor-lines when infill stud-wall construction <sup>1</sup> is employed for exterior wall construction.
Cavity Insulation - Use either 1 or combination of 1 and 2	<p>1 - Full cavity depth or less of Staycell ONE STEP® 502 HFO using sheathing as substrate and covering the width of the cavity and inside the stud flange.</p> <p>2 - Any non-combustible insulation (if batts, may be faced or unfaced)</p>
Exterior Sheathing - Use either 1 or 2	<p>1 - 1/2-inch thick, exterior type gypsum sheathing</p> <p>2 - 5/8-inch thick, exterior type gypsum sheathing</p>
Exterior Insulation - Use either 1 or 2	<p>1 - None</p> <p>2 – Staycell ONE STEP® 502 HFO - Total thickness to be a maximum of nominal 4 inches.</p>
Exterior Wall Covering Use either 1, 2, 3, 4, 5 or 6	<p>1 - Brick - Standard nominal 4-inch thick, clay brick. Installed with brick veneer anchors - standard types - installed maximum 24 inches OC vertically on each stud. A maximum 2-inch air gap between exterior insulation and brick.</p> <p>2 - Stucco - Minimum 3/4-inch thick, exterior cement plaster and lath. The secondary water-resistive barrier (WRB) may be installed between the exterior insulation and the lath. The secondary WRB shall not be full-coverage asphalt or butyl-based self-adhered membranes.</p> <p>3 - Minimum 2-inch thick Limestone, natural stone, or minimum 1 1/2-inch thick cast artificial stone. Any standard non-open jointed installation technique such as shiplap, etc. may be used.</p> <p>4 - Terracotta Cladding – Use any terracotta cladding system in which the terracotta is a minimum of 1 1/4-inches thick. Any standard non-open-jointed installation technique such as shiplap, etc. may be used.</p> <p>5 - Minimum 1-inch thick, Clark Pacific glass-fiber-reinforced-concrete (GFRC) panels. Standard installation techniques may be used. Staycell ONE STEP® 502 HFO sprayed onto the interior face of the GFRC panel up to a maximum of 4 inches.</p> <p>6 - Minimum 1-inch thick, Gates Precast Liter precast panels. Standard installation techniques may be used. Staycell ONE STEP® 502 HFO Sprayed onto the interior face of the precast concrete panels up to a maximum of 4 inches.</p>
Window/Door Perimeters	Framed as required for the base wall. Use No. 25 gauge (minimum) sheet steel for flashing area outside of the base wall.

<sup>1</sup>. Infill stud wall construction refers to the condition where the stud framing of an exterior wall is interior to the floor line slab edges, effectively terminating the stud cavity at each floor-line and creating sectioned stud bays in between sequential floors.

